



Medicament Delivery Device with Moisture Resistant Coating (CLEAN COPY)

Technical Field

This invention relates to a novel form of reservoir means, such as a medicament
5 capsule and the like and to a delivery device e.g. an inhaler, for use in administering a
medicament in such a reservoir means.

Background Art

Many medicament delivery devices, such as inhalers, make use of medicament in a
10 finely divided powder form. The powder may be located within the delivery device, for
instance, in a single storage compartment or in a plurality of single dose locations.

One form of inhaler may make use of medicament powder which is located within a
frangible, plastic capsule. In use, the capsule is inserted into the inhaler and operation of the
inhaler ruptures from the plastic capsule so that the powder may be extracted from the
15 capsule and inhaled by the user.

A problem encountered with many such devices making use of powdered
medicament is that, if moisture comes into contact with the powder, it will tend to make it
less free-flowing and therefore render the operation of the device less effective because the
correct dose of powder cannot be fully delivered.

20 Moisture may access the powder via several different mechanisms. These include the
passage of the moisture through, for example, the plastic wall of encapsulated powder for
those inhalers which make use of capsules loaded with medicament powder. For those
inhalers which include a storage compartment loaded with powder and from which a dose of
powder is accessed by some form of moving part within the inhaler and then presented to an
25 air passageway for inhalation, moisture can access powder within the storage compartment
by finding its way along a gap or gaps between the moving parts. In some inhalers there is

the possibility of a "wick" type path being established between the powder in a storage compartment within the inhaler and a location within the inhaler where a dose of medicament is located.

5 With inhalers where a plurality of single doses of medicament is located within the inhaler, there is again likely to be one or more moving parts, providing gaps along which moisture may travel to access each individual dose of medicament.

It is also possible that moisture can pass through the plastic walls of inhalers and reach the powder contained within the inhaler whether in a single storage compartment or in individual dosage locations.

10 International Patent Application No WO 00/1216-31 describes the use of a Parylene coating on the inner surface of the metering chamber which is intended to mitigate the deposition of medicament particles on the inner walls of a metered dose inhaler (MDI) for the delivery of medicament via a pressurised aerosol.

Summary of the Invention

15 A moisture resistant coating, e.g., a Parylene coating, may be used as on a medicament reservoir and/or a medicament delivery device, such as an inhaler (e.g., a dry powder inhaler), to render the device, and especially the medicament chamber, moisture resistant. A reservoir means is provided with a moisture resistant coating in an embodiment of the invention. The reservoir means may be any conventionally known reservoir means,
20 such as a bulk medicament reservoir or one or more single dose reservoir means or a spool and spool carrier. The reservoir means is coated on the outer walls, such that the reservoir means is substantially sealed in the coating and is rendered moisture proof.

In another embodiment of the invention, a medicament delivery device which comprises a medicament reservoir, a medicament delivery passage and a metering member
25 characterised in that the device is provided with a moisture resistant coating on one or more surfaces is provided. Preferably, the whole of the device is substantially provided with a moisture resistant coating.

The moisture resistant coating is preferentially a biocompatible coating. Such coatings include, but are not limited to, sugars.

Brief Description of the Drawings

The foregoing features of the invention will be more readily understood by reference to the following detailed description, taken with reference to the accompanying drawings, in which:

5 Fig. 1 depicts an embodiment of the invention that is a medicament delivery device (e.g., an inhaler) with a reservoir means, a metering member, and a medicament delivery passage, various surfaces of which are coated with a moisture resistant coating;

 Fig. 2A depicts a side view of an embodiment of the invention that is an inhaler utilizing a cartridge holding a plurality of capsules, each capsule containing a single dose of
10 medicament metered by a spool;

 Fig. 2B depicts a view of a cartridge with a plurality of spool carriers for use in an embodiment of the invention; and

 Fig. 2C depicts a spool for use with the cartridge depicted in Fig. 2B, according to an embodiment of the invention.

Detailed Description of Specific Embodiments

 We have now surprisingly found that a moisture resistant coating, e.g., a Parylene coating, may be used as on a medicament reservoir and/or a medicament delivery device, such as an inhaler, to render the device, and especially the medicament chamber, moisture resistant.

20 According to a first aspect of the invention we provide a reservoir means which means is provided with a moisture resistant coating.

 In a preferred embodiment, the reservoir means contains medicament such that the reservoir means may be used in conjunction with a delivery device.

 The reservoir means may be any conventionally known reservoir means, such as a
25 bulk medicament reservoir or one or more single dose reservoir means. The reservoir means shall not include a pressurised canister for use in inhalation therapy as described in the prior art. When the reservoir means is a single dose reservoir, such as a capsule, e.g., a conventional gelatin capsule, or a spool and spool carrier as described in International Patent

Application No. W093/16748 (as depicted in Figure 1), the coating may be on the inner walls or the outer walls of the reservoir means. However, preferably, the reservoir means **44** is coated on the outer walls **60**, such that the reservoir means **44** is substantially sealed in the coating **60** and is rendered moisture proof. In such a case, the cartridge may also be provided
5 with a moisture resistant coating.

According to a further feature of the present invention, we provide a medicament delivery device which comprises a medicament reservoir as hereinbefore described.

In an especially preferred embodiment the medicament delivery device **80** is also provided with a moisture resistant coating **50**. Such a coating preferentially covers
10 substantially the whole of the delivery device.

When the medicament reservoir means comprises a bulk reservoir, then the medicament delivery device may preferentially include a metering member **41**. The metering member **41** preferably is also provided with a moisture resistant coating.

According to a yet further feature of the invention we therefore provide a medicament
15 delivery device which comprises a medicament reservoir, a medicament delivery passage **45** and a metering member characterised in that the device is provided with a moisture resistant coating on one or more surfaces. Preferably, the whole of the device is substantially provided with a moisture resistant coating.

The moisture resistant coating may be provided on one or more external or internal
20 surfaces of the body of the medicament delivery device. The moisture resistant coating preferentially coats one or more surfaces of the bulk medicament reservoir. Other surfaces of the body of the medicament delivery device may also be provided with a moisture resistant coating.

The moisture resistant coating may be in the form of any material which is effective
25 to prevent moisture accessing the powder **20**. Typically, it may be applied to those surfaces between which there may be a gap due to relative movement between the surfaces when the inhaler is in use. However, the moisture resistant coating may be applied additionally or alternatively to other surfaces including the whole or part of the external surface of the

inhaler in order to prevent moisture passing into the interior of the inhaler through the walls thereof.

The moisture resistant coating should, of course, be sufficiently stable and robust so that damage to the coating during use of the delivery device.

5 The moisture resistant coating of the invention may be applied to any conventionally known medicament delivery system. However, in a preferred embodiment, the medicament delivery device is an inhaler. Whilst the moisture proof barrier may be applied to any conventionally known inhaler, it is an especially preferred aspect of the invention for the inhaler to be a dry powder inhaler (DPI).

10 Thus, in a preferred embodiment we provide an inhaler, e.g., a DPI, in which the medicament reservoir is provided with a moisture resistant coating.

Dry powder inhalers are known, such as TECHNOHALER, being developed by Innovata Biomed in the UK. As depicted in Figs. 2A – 2C, WO 93/16748 describes an inhaler **140** which comprises a disc-like cartridge having a plurality of medicament carrying capsules **127** around its periphery. Each capsule **127** comprises a spool carrier **129** which
15 houses a spool **125**. Each spool **125** has a flange **124** at each end which form a tight slidable fit within the body of the spool carrier **129**. The space left between the body of the spool **125** and the spool carrier **129** is filled with an appropriate medicament.

In a preferred embodiment, an example of which is depicted by Figs. 2A – 2C, we
20 provide a dry powder inhaler **140** wherein the medicament reservoir comprises one or more individual medicament capsules **127**, e.g. spool carriers **129** and wherein each medicament capsule **127** is provided with a moisture resistant coating. Preferably, the medicament capsule is sealed in a moisture resistant coating.

A variety of medicaments may be administered by using the inhaler of the invention.
25 Such medicaments are generally (but not limiting), bronchodilators I or other anti asthma drugs or antibiotics. Such medicaments include, but are not limited to β_2 -agonists, e.g., fenoterol, formoterol, pirbuterol, reproterol, rimiterol, salbutamol, salmeterol and terbutaline; non-selective beta-stimulants such as isoprenaline; xanthine bronchodilators, e.g.,

theophylline, aminophylline and choline theophyllinate; anticholinergics, e.g., ipratropium bromide; mast cell stabilisers, e.g., sodium cromoglycate and ketotifen; bronchial anti-inflammatory agents, e.g., nedocromil sodium; and steroids, e.g., beclomethasone dipropionate, fluticasone, budesonide and flunisolide; and combinations thereof.

5 Specific combinations of medicaments which may be mentioned include combinations of steroids, such as, beclomethasone dipropionate, fluticasone, budesonide and flunisolide; and combinations of to β_2 -agonists, such as, formoterol and salmeterol. It is also within the scope of this invention to include combinations of one or more of the aforementioned steroids with one or more of the aforementioned β_2 -agonists.

10 Further medicaments may include proteinaceous compounds and/or macromolecules, for example, leuprolide and alpha interferon; hormones, such as insulin, human growth hormone, parathyroid hormone; growth factors, anticoagulants, immunomodulators, cytokines and nucleic acids.

15 According to a yet further feature of the invention we provide a method of treating a respiratory disorder which comprises the administering of a therapeutically effective amount of a pharmaceutically active agent to a patient suffering from such a disorder.

 The moisture resistant coating is preferentially a biocompatible coating. Such coatings include, but are not limited to, sugars.

20 Polymers of poly-para-xylylenes are known as parylene. This material is a conformal polymer film which has been used in a number of applications, including electronics circuits and sensor, where environmental and dielectric isolation is required.

 We further the use of a parylene in the manufacture of a moisture resistant capsule as hereiribefore described.

25 Parylenes are thermoplastic polymers that are capable of polymerising on surfaces from an active monomer gas, without the presence of a liquid. The process is capable of producing very thin layers of polymer and, indeed, a layer of from 10 to 20 microns may be sufficient to protect inhalers and their parts from ingress of moisture.

The polymerisation process takes place at room temperature without solvents and additives. Since the parylene is applied as a gas it conforms to the topography of the surface which it contacts. Since the process does not involve a liquid phase, there is no pooling and bridging during application. The coating is free of pinholes even if the coating has a
5 thickness of less than one micron. As well as being resistant against moisture, parylene is also resistant against other media including hydrocarbons, acids and blood.

The coating may be applied in a single vacuum-coating operation in a thickness from 0.025 to 75 microns and can be controlled accurately to $\pm 10\%$ of the final thickness.